



## GREASE COMPATIBILITY CHART

	Aluminum Complex	Barium Complex	Calcium Stearate	Calcium 12-Hydroxy	Calcium Complex	Calcium Sulfonate Complex	Clay (Non-Soap)	Lithium Stearate	Lithium 12-Hydroxy	Lithium Complex	Polyurea (Conventional)	Polyurea Shear (Stable)
Aluminum Complex	-	I	I	C	I	B	I	I	I	B	I	C
Barium Complex	I	-	I	C	I	C	I	I	I	I	I	B
Calcium Stearate	I	I	-	C	I	C	C	C	B	C	I	C
Calcium 12-Hydroxy	C	C	C	-	B	B	C	C	C	C	I	C
Calcium Complex	I	I	I	B	-	I	I	I	I	C	C	C
Calcium Sulfonate Complex	B	C	C	B	I	-	I	B	B	C	I	C
Clay (Non-Soap)	I	I	C	C	I	I	-	I	I	I	I	B
Lithium Stearate	I	I	C	C	I	B	I	-	C	C	I	C
Lithium 12-Hydroxy	I	I	B	C	I	B	I	C	-	C	I	C
Lithium Complex	B	I	C	C	C	C	I	C	C	-	I	C
Polyurea (Conventional)	I	I	I	I	C	I	I	I	I	I	-	C
Polyurea (Shear Stable)	C	B	C	C	C	C	B	C	C	C	C	-

### Relative Compatibility Rating

**B = Borderline**

**C = Compatible**

**I = Incompatible**

**NOTE:** This chart is a general guide to compatibility. Specific properties of greases can dictate compatibility. Testing should be done to determine if greases are compatible.



Authorized Distributor  
 Calx Trading Corporation  
 1245 Amaranth Dr.  
 Naperville, IL 60564  
 Tel: 630-677-7241  
 Cell: 630-456-6721  
 www.calxtrading.com